

RAPID FILLER

DEFINITION

Two-component general-purpose polyester putty containing fine-grain aluminum. Once applied, it offers good vertical hold and easy sandability. Suitable for treating the bodywork of cars, trucks, industrial vehicles, and similar types.

Recommended for use on fiberglass and metal substrates, especially for high-build applications, as an alternative to tin soldering.

CHARACTERISTICS

- Chemical nature: unsaturated polyester resin
- Color: straw yellow
- Appearance: fine-grain
- Density: 1,71 g/cm³ ± 0.05
- Thermal resistance up to 120-140°C

SUBSTRATE PREPARATION

Surfaces must be thoroughly degreased, sanded, clean, and dry. Suitable for application on:

- Bare metal
- Previously painted surfaces sanded with P80
- Fiberglass

Before application, it is recommended to carry out preliminary tests to verify the product's compatibility with the surface to be treated, considering the wide variety of application conditions and materials available on the market.

PREPARATION OF THE MIXTURE

Catalyze with 2–3% by weight of paste hardener.

Avoid using excessive amounts of hardener, as it may cause peroxide staining during the painting phase.

POT-LIFE

At 20°C: 6 ± 2 minutes

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.

APPLICATION

Apply with a spatula.

Do not apply at temperatures below 5°C.

SANDING

Minimum sanding time:

- Air drying at 20°C: 30 minutes
- With IR lamp: 10 minutes

Sanding sequence: P80-P220.

OVERPAINTING

Can be overcoated with any type of filler.

Due to the variety of painting systems and application conditions, it is recommended to carry out preliminary tests to verify the compatibility of the chosen paint system with the applied product.

Each cycle should be evaluated in advance, as the variables involved can significantly affect the final result.

STORAGE

Store the product in a dry place, protected from direct sunlight, at temperatures between 5°C and 30°C.

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.