

POKER

DEFINITION

Single-component protective coating, sound-deadening and anti-chip, based on acrylic resins, bitumen-free. Formulated for the protection of underbodies, side skirts/rocker panels, wheel arches, and for the refinishing of sections in engine compartments and luggage/boot compartments.

CHARACTERISTICS

- Chemical nature: acrylic resins in solution
- Density: $1.27 \pm 0.03 \text{ g/cm}^3$
- Colour: white, gray, black
- Non volatile content: $57\% \pm 2$
- Yield: 2-2.5 m²/l

SUBSTRATE PREPARATION

Wash and degrease the surface to be treated very thoroughly with nitro thinner.

Before application, preliminary tests are recommended to verify the product's compatibility with the surface to be treated, considering the wide variety of application conditions and materials available on the market.

APPLICATION

Product is ready to use, no dilution required. Shake the product before use. Apply with a Poker gun with adjustable nozzle (code 85108) that can be screwed directly onto the can, or with a pressure gun (code 85117). Working pressure at the regulator: 4/5 atm maximum.

Do not apply at temperatures below 5°C.

DRYING TIME

- Dust free (20°C): 5 minutes
- Complete drying (20°C): 20-30 minutes depending on the thickness applied.

OVERPAINTING

Can be overcoated after drying and sanding with water-based basecoats, or after a brief flash-off time with solvent-

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.

based basecoats.

Before application, preliminary testing is recommended to verify the product's compatibility with the surface to be treated, considering the wide variety of application conditions and materials available on the market.

STORAGE

Store the product in a dry environment, away from direct sunlight, at temperatures between 5°C and 30°C.

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.

GELSON S.r.l.

Lainate (Milan) 20045 Italy - Via Varese 11/13
TEL +39 029370640
FAX +39 0293570880
MAIL info@gelson.it

