

PRIMER PER PLASTICHE

DEFINITION

High-performance, one-component, transparent spray primer for polyolefin plastics (PP, PE, TPO, EPDM) and rubber in general. It can be used for coating all kinds of plastic parts, not treated at the origin, employed in automotive industry and beyond. Ideal for application on car and motorcycle bumpers and side trims.

CHARACTERISTICS

- Chemical nature: solution of adhesion promoters/resins in solvent
- Appearance: clear liquid
- Color: colorless
- Theoretical yield: 0.5–1 m²/spray can at 1 micron dry film thickness

SUBSTRATE PREPARATION

Surfaces must be perfectly degreased, clean, and dry. Completely remove any previous sealants, silicone, oil, and dust.

Applicable on polyolefin plastics: polypropylene (PP), polyethylene (PE), thermoplastic olefins (TPO), ethylene propylene diene monomer (EPDM).

If necessary, apply masking tape to all edges of the part to be protected. Lightly sand the area with an abrasive pad (Kofle-x) and clean.

Before application, it is recommended to carry out preliminary tests to verify the compatibility of the product with the surface to be treated, considering the wide variety of application conditions and materials available on the market.

APPLICATION

Shake the can for at least 30 seconds before application. Apply the Plastic Primer in two light coats. The primer makes the substrate paintable for a limited time only (6–12 hours). If this time passes without overcoating, a new application will be necessary.

After use, turn the can upside down and spray for 2–3 seconds to clean the nozzle and prepare the can for future use. Do not apply at temperatures below 5°C.

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.

OVERPAINTING

Allow to flash-off for at least 20 minutes at 20°C before overcoating.

Can be overcoated with all one-component and two-component primers, fillers, and topcoats within one hour after flashing off, to achieve optimal results.

Due to the wide variety of paint systems and application conditions, it is recommended to carry out preliminary tests to verify compatibility between the selected paint system and the applied product. Each cycle must be evaluated in advance, as various factors can significantly affect the final result.

STORAGE

Store the product in a dry place, protected from direct sunlight, at temperatures between 5°C and 30°C.

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.

GELSON S.r.l.

Lainate (Milan) 20045 Italy - Via Varese 11/13
TEL +39 029370640
FAX +39 0293570880
MAIL info@gelson.it

